



## DATA SHEET

### 8331 AROMATIC MOISTURE CURE URETHANE

---

**ULTRADEC**

#12 Tenbrook Industrial Park Arnold, MO 63010  
Office 636.296.2900 Fax 636.296.2904  
[www.ultradec.com](http://www.ultradec.com) [info@ultradec.com](mailto:info@ultradec.com)

#### **DESCRIPTION:**

8331 is a single component; clear aromatic urethane coating that is cured upon exposure to ambient moisture in the air. No catalyst is necessary with this formulation.

#### **USE:**

Recommended for interior use. The wearing finish over non-bleeding wood surfaces, non-lifting flooring material, and over Ultradec Epoxy Base Coats.

#### **MIXING:**

Use as received from container. Store open containers upside down with lid tightly secured.

#### **APPLICATION:**

Apply with pure china bristle brush, 1/4" roller cover, Lambswool Applicator, squeegee, or trowel. Turn off all pilot lights. Flash point 77° F. Use with adequate ventilation.

#### **SPREADING RATE:**

200-300 square feet per gallon. One coat equals approximately 2.5 mils dry. DO NOT PUDDLE!

#### **CLEAN UP:**

Methyl Ethyl Ketone (MEK) or Xylene (Xylol)

#### **DRY TIME:**

1 1/2 - 2 1/2 hours between coats. 12 hours for light traffic.

#### **SAFETY PRECAUTIONS:**

Keep out of reach of children. Harmful if taken internally. Provide proper and adequate ventilation. Exposure to vapors should be avoided for prolonged periods of time. Applicator should wear NIOSH approved vapor absorbing mask. Keep away from open flames. Avoid prolonged contact with skin. After materials have been cleaned from skin, wash with soap and water. No smoking in application area. Flammable.

#### **NON-WARRANTY:**

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without any warranties, expressed or implied, since conditions and methods of use of our product are beyond our control. We recommend that the prospective user determine the suitability of our materials for the intended use before adopting them.