



DATA SHEET

8339

ALIPHATIC MOISTURE CURE URETHANE

ULTRADEC

#12 Tenbrook Industrial Park – Arnold, MO 63010

Office 636.296.2900 Fax 636.296.2904

www.ultradec.com info@ultradec.com

DESCRIPTION:

8339 is a single component, 42% Non-yellowing urethane coating that is cured upon exposure to ambient moisture in the air.

USE:

The wearing finish over non-bleeding wood surfaces and as a glaze coat over Ultradec's vinyl chip or colorquartz aggregate systems.

MIXING:

Use as received from container. Store upside down with lid tightly secured.

APPLICATION:

Apply with a pure china bristle brush, short nap roller, Lambswool Applicator, or squeegee. If using a roller, be sure to roll in one direction so as not to incorporate bubbles into the glaze coat.

SPREADING RATE:

250-300 square feet per gallon. One coat equals approximately 2.5 mils dry. **DO NOT PUDDLE!**

CLEAN UP:

Methyl Ethyl Ketone (MEK) or Xylene (Xylol)

DRY TIME:

1 1/2 - 2 1/2 hours between coats. 12 hours for light traffic.

SAFETY PRECAUTIONS:

Keep out of reach of children. Harmful if taken internally. Provide proper and adequate ventilation. Exposure to vapors should be avoided for prolonged periods of time. Applicator should wear NIOSH approved vapor absorbing mask. Keep away from open flames. Avoid prolonged contact with skin. After materials have been cleaned from skin, wash with soap and water. No smoking in application area. **Flammable.**

NON-WARRANTY:

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without any warranties, expressed or implied, since conditions and methods of use of our product are beyond our control. We recommend that the prospective user determine the suitability of our materials for the intended use before adopting them.