



TECHNICAL DATA SHEET

8331 AROMATIC MOISTURE CURE URETHANE

ULTRADEC

#12 Tenbrook Industrial Park – Arnold, Mo 63010

Office 636-296-2900 Fax 636-296-2904

www.ultradec.com info@altradec.com

DESCRIPTION:

A single component 42% solids Moisture Cure Urethane, which cures by reaction with ambient moisture in the air to a hard clear film with outstanding abrasion resistance, toughness, and flexibility. It is recommended for interior use on natural or stained hardwood floors and prepared bare concrete. When staining wood with a white or pastel stain, use Ultradec's 8339 Non-Yellowing Moisture Cure Urethane Glaze.

PHYSICAL PROPERTIES (Cured at 70° F, 70% R.H.):

Color	Clear
Odor	Of Solvent
Bulk Density	8.0 lbs approx.
Solvent	Xylene
Flash Point	77° F (Seta CC)
Non-Volatile Matter	44%
Dry time (tack free)	2 1/2 hours
Sward Hardness	(1 day) 23
	(1 week) 26
Abrasion Resistance	(Taber)
	(CS-17 Wheel, 1,000 g., 1,000 cycles) 1.0 mg Loss
Tensile Strength	3500 psi
Elongation	150%
Impact Resistance	160-inch tbs.
Mandrel Flexibility	passes 1/8"
Coverage	250 - 300 sq-ft/gal
Thickness per Coat	2.5 mils

NON-WARRANTY:

These suggestion and data are based on information we believe to be reliable. They are offered in good faith, but without any warranties, expressed or implied, since conditions and methods of use of our product are beyond our control. We recommend that the prospective user determine the suitability of our materials for the intended use before adopting them. Keep out of reach of children.